



3.0 oz Gray Premium Grade Spunbond Polyester

Size	Weight (lbs)	Cs Pk
3'x300'	22.5	5
4'x300'	30.26	5
5'x300'	38	5
6'x300'	44.35	5
7'x300'	53.44	5
9'x300'	67.53	5
12'x300'	90.70	3
3'x50'	88.32	24
3'x200'	88.32	6
4'x100'	105	12
4'x150'	88.32	6
4'x200'	105	6

Specs	ASTM Test Method	Result	Units of Measurement
Basis Weight Thickness	D-3776	3.0 21.0	Ounces/square yard mils
Grab Tensile Strength (MD/TD)	D-4632	79/74	Pounds
Grab Elongation (MD/TD)	D-4632	52/56	%
Trapezoidal Tear Strength (MD/TD)	D-4533	35.5/39	Pounds
Water Flow Rate	D-4491	275	Gallons/minute/square feet
Puncture Strength	D-4833	45.1	Pounds
Burst Strength	D-3786	122	Pounds per square inch
UV Degradation (150 hour accelerated weather test)	D-4355	75	% of fabric retained